



TECHNICAL DATA SHEET

PUR95A

1730 NE Miller Street
 McMinnville, OR 97128
 (503) 434-5561

Properties		Test Method	Typical Value English
Specific Gravity	gr./cm ³	ASTM D-792	1.120
Hardness	Shore A	ASTM D-2240	95A
Tensile Strength	psi/MPa	ASTM D-412	5400 psi
Tensile Stress	@100% Elong.	ASTM D-412	2800 psi
Elongation at Break	%	ASTM D-412	300%
E-Modulus	psi/MPa	ASTM D-412	5000 psi
Tear Strength	lb./in. N/mm	ASTM D-624, Die C	930 lb./in.
Taber Abrasion Resistance / mg loss	1000 gr./H-18	ASTM D-1044	30 mg
Processing Conditions, Extrusion	°F/°C		360-420°F

This information has been gathered from standard reference materials and/or test data that is believed to be accurate and reliable. Nothing herein shall be deemed to be a warranty or representation, express or implied, with respect to the use of such information or the use of the goods described for any particular purpose alone or in combination with other goods and/or processes, or that their use does not conflict with existing patent rights. No license is granted to practice any patented invention. It is offered solely for your consideration, investigation, and verification.