

# CarTech® 316L-SCQ® Stainless

## Identification

UNS Number

• S31603

## Type Analysis

Single figures are nominal except where noted.

<b>Carbon (Maximum)</b>	0.03 %	<b>Manganese</b>	0.25 to 2.00 %
<b>Phosphorus (Maximum)</b>	0.045 %	<b>Sulfur</b>	0.010 to 0.015 %
<b>Silicon (Maximum)</b>	1.00 %	<b>Chromium</b>	16.00 to 18.00 %
<b>Nickel</b>	10.00 to 14.00 %	<b>Molybdenum</b>	2.00 to 3.00 %
<b>Iron</b>	Balance		

## General Information

### Description

CarTech 316L-SCQ stainless is an austenitic stainless designed for use where extremely good surface finishes are required. The corrosion resistance and mechanical properties of CarTech 316L-SCQ stainless are similar to CarTech 316L. Typical specifications for bar products are ASTM A-276 and SEMI F20.

CarTech 316L-SCQ stainless is produced to a tightly controlled chemical composition within conventional analysis limits CarTech 316L. Carefully selected melt stock is utilized to restrict the occurrence of typical residual elements. One important element, sulfur (S), influences inclusion count, machinability and weldability, and can be varied according to customer specification. The intermediate sulfur range is controlled to 0.005 to 0.015% for a unique combination of weldability and micro-cleanness. For the ultra-pure composition, sulfur is held in the range of 0.001 to 0.004% maximum. Either of the compositions may be melted by air melting + Vacuum Arc Remelting (AOD+VAR) or by Vacuum Induction Melting + Vacuum Arc Remelting (VIM+VAR) depending on the level of micro-cleanness required.

### Applications

CarTech 316L-SCQ stainless could be considered for use in applications where cleanliness, resulting in reduced inclusions, is advantageous in thin-wall components such as valves and fittings.

Industries in which this alloy could be considered for applications include semiconductor, nuclear, biopharmaceutical, aerospace, and chemical and gas processing.

## Corrosion Resistance

Due to its superior corrosion resistance, the use of 316L-SCQ stainless has been extended to handling many of the gasses used in semiconductor manufacturing and chemicals used by chemical process industries.

The alloy is more resistant to pitting than conventional 18-8 alloys.

For optimum corrosion resistance, surfaces must be free of scale, coatings applied for drawing and heading, lubricants and foreign particles. After fabrication of parts, cleaning and/or passivation should be considered.

## CarTech® 316L-SCQ® Stainless

**Important Note:** The following 4-level rating scale is intended for comparative purposes only. Corrosion testing is recommended; factors which affect corrosion resistance include temperature, concentration, pH, impurities, aeration, velocity, crevices, deposits, metallurgical condition, stress, surface finish and dissimilar metal contact.

Nitric Acid	Good	Sulfuric Acid	Moderate
Phosphoric Acid	Moderate	Acetic Acid	Good
Sodium Hydroxide	Moderate	Salt Spray (NaCl)	Good
Sea Water	Moderate	Sour Oil/Gas	Moderate
Humidity	Excellent		

## Properties

### Physical Properties

Specific Gravity	7.95
Density	0.2870 lb/in <sup>3</sup>
Mean Specific Heat	0.1200 Btu/lb/°F
Mean CTE	10.3 x 10 <sup>-6</sup> in/in/°F
Electrical Resistivity	445.0 ohm-cir-mil/ft

## Heat Treatment

### Annealing

Heat to 1850/2050°F (1010/1121°C) and water quench. Brinell hardness approximately 150.

### Hardening

Cannot be hardened by heat treatment. Hardens only by cold working.

## Workability

### Hot Working

316L-SCQ stainless can be readily forged, upset and hot headed.

### Forging

To forge, heat uniformly to 2100/2300°F (1149/1260°C). Do not forge below 1700°F (927°C). Forgings can be air cooled.

Best corrosion resistance is obtained if the forgings are given a final anneal.

### Cold Working

316L-SCQ stainless can be deep drawn, stamped, headed and upset without difficulty. Since this alloy work hardens, severe cold forming operations should be followed by an anneal.

### Machinability

316L-SCQ stainless machines with chip characteristics that are tough and stringy. The use of chip curlers and breakers is advised. Since the austenitic stainless grades work harden rapidly, heavy positive feeds should be considered.

Many customers prefer a small amount of cold work to enhance machinability and achieve a better chip characteristic and as-machined surface finish. The process of cold drawing increases the yield strength and tensile strength and decreases percent elongation and percent reduction of area. To accommodate cold work to improve machinability, many customer specifications allow a decrease in the percent elongation requirement to 20% minimum.

Since machinability means different things to different shops (speeds and feeds, tool life, surface finish, etc.), each shop needs to run comparative tests to establish optimum machining parameters for a particular sulfur level and to generate cost data. Usually, the lower the sulfur levels, the greater the tendency to burnish the surface, which improves surface luster. Also, the lower the inclusion content, the better the surface after electropolishing.

**Typical Machining Speeds and Feeds—Type 316L-SCQ Stainless**

The speeds and feeds in the following charts are conservative recommendations for initial setup. Higher speeds and feeds may be attainable depending on machining environment.

**Turning—Single-Point and Box Tools**

Depth of Cut (Inches)	Micro-Melt® Powder High Speed Tools			Carbide Tools (inserts)			
	Tool Material	Speed (fpm)	Feed (lpr)	Tool Material	Speed (fpm)		Feed (lpr)
					Uncoated	Coated	
<b>Annealed</b>							
.150	M48, T15	50	.010	C6	290	330	.010
.025	M48, T15	65	.005	C6	315	365	.005
<b>Cold Drawn</b>							
.150	M48, T15	40	.010	C6	275	295	.010
.025	M48, T15	55	.005	C6	295	325	.005

**Turning—Cut-Off and Form Tools**

Tool Material		Speed (fpm)	Feed (lpr)						
Micro-Melt® Powder High Speed Tools	Carbide Tools		Cut-Off and Form Tools Width (inches)						
			1/16	1/8	1/4	1/2	1	1 1/2	2
<b>Annealed</b>									
M48, T15	C6	45	.0010	.0011	.0013	.0018	.0010	.0008	.0005
		195	.0010	.0011	.0013	.0018	.0010	.0008	.0005
<b>Cold Drawn</b>									
M48, T15	C6	40	.0010	.0011	.0013	.0018	.0010	.0008	.0005
		185	.0010	.0011	.0013	.0018	.0010	.0008	.0005

**Rough Reaming**

Micro-Melt® Powder High Speed Tools		Carbide Tools		Feed (lpr) Reamer Diameter (Inches)					
Tool Material	Speed (fpm)	Tool Material	Speed (fpm)	1/8	1/4	1/2	1	1 1/2	2
<b>Annealed</b>									
M48, T15	20	C6	30	.0008	.0009	.0009	.0010	.0011	.0013
				.0008	.0009	.0009	.0010	.0011	—
<b>Cold Drawn</b>									
M48, T15	15	C6	25	.0008	.0009	.0009	.0010	.0011	.0013
				.0008	.0009	.0009	.0010	.0011	—

**Drilling**

Tool Material		Speed (fpm)	Feed (Inches per revolution) Nominal Hole Diameter (Inches)							
Micro-Melt® Powder High Speed Tools	Carbide Tools		1/16	1/8	1/4	1/2	3/4	1	1 1/2	2
<b>Annealed</b>										
M42	C6	20-40	.0008	.001	.002	.004	.006	.007	.007	.008
		50-90	.0007	.001	.002	.004	—	.007	.008	—
<b>Cold Drawn</b>										
M7	C6	15-35	.0006	.001	.002	.004	.006	.007	.007	.008
		40-80	.0006	.001	.002	.004	—	.007	.008	—

End Milling—Peripheral

Depth of Cut (inches)	Micro-Melt® Powder High Speed Tools						Carbide Tools					
	Tool Material	Speed (fpm)	Feed (ipt) Cutter Diameter (inches)				Tool Material	Speed (fpm)	Feed (ipt) Cutter Diameter (inches)			
			1/4	1/2	3/4	1-2			1/4	1/2	3/4	1-2
<b>Annealed</b>												
.050	M48, T15	40	.001	.002	.004	.006	C6	150	.001	.002	.004	.006
<b>Cold Drawn</b>												
.050	M48, T15	35	.001	.002	.004	.006	C6	150	.001	.002	.004	.006

Slot Milling—Peripheral

Depth of Cut (inches)	Micro-Melt® Powder High Speed Tools			Carbide Tools (inserts)		
	Tool Material	Speed (fpm)	Feed (ipr)	Tool Material	Speed (fpm)	Feed (ipr)
<b>Annealed</b>						
.050	M48, T15	42	.003	C6	166	.003
.150		35	.0045		130	.0045
<b>Cold Drawn</b>						
.050	M48, T15	36	.003	C6	150	.003
.150		30	.0045		115	.0045

Tapping

High Speed Tools	
Tool Material	Speed (fpm)
<b>Annealed</b>	
M7, M10	10-15
<b>Cold Drawn</b>	
M7, M10	8-13

Broaching

Micro-Melt® Powder High Speed Tools		
Tool Material	Speed (fpm)	Chip Load (ipt)
M48, T15	12	.002
M48, T15	10	.002

Additional Machinability Notes

Figures used for all metal removal operations covered are averaged. On certain work, the nature of the part may require adjustment of speeds and feeds. Each job has to be developed for best production results with optimum tool life. Speeds or feeds should be increased or decreased in small steps.

Weldability

316L-SCQ alloys are readily welded using Gas Tungsten Arc, Plasma, Laser and Electron Beam Welding techniques. Extra attention should be paid, however, to the weld penetration and bead geometry because of the effects on sulfur on the physics of the weld puddle. The penetration ratio (ratio of depth to bead width) increases with an increase in sulfur content up to about .03%. Conversely, the weld bead will become shallow and broader as the sulfur content decreases. The weld bead geometry and location can be a problem if components with significantly different sulfur levels are joined. Where possible, it is suggested that both components have similar sulfur contents. When this is not possible, good welds are possible between two components with significantly lower sulfur (0.004% vs.: 0.008 % sulfur) through carefully positioning the welding electrode and selection on the shielding gases.

316L-SCQ stainless can be satisfactorily welded by the shielded fusion and resistance welding processes. Since austenitic welds do not harden on air cooling, the welds should have good toughness.

Oxyacetylene welding is not recommended since carbon pickup in the weld may occur.

The alloy can be welded without loss of corrosion resistance due to intergranular carbide precipitation. Usually the alloy can be used in the as-welded condition. However, for service in the most severe environments, the welded structure should be reannealed after welding.

Where a filler metal is required, AWS E/ER316L welding consumables should be considered.

Micro-Cleanness

Cleanness is evaluated by means of a microscopic examination of a sample to establish a "J-K" rating. Carpenter typically conducts this evaluation on billets in accordance with ASTM E-45 Method A with ratings based on Plate III. Samples are rated from the top and

bottom of the first, middle and last ingot of the heat. The limits contained in the hyperlink entitled "Micro-Cleanliness Single Vacuum Melt" are acceptable for air melt plus vacuum arc remelted 316L-SCQ stainless (AOD + VAR) with 0.005/0.015% sulfur.

The reason we are offering only a single vacuum melt (AOD + VAR) and no guarantee on Category A inclusions (sulfides) is that when sulfur is added to meet the intermediate sulfur level, it is obvious that the level of sulfide inclusions will increase. We have, in fact, seen values up to a rating of 3 in Category A Thin in some heats.

The cleanest version of 316L-SCQ stainless utilizes two vacuum melting techniques, in combination with restricting sulfur to 0.004% maximum. In all other respects, this material has the same chemical balance and mechanical property capability as the single vacuum melted (AOD + VAR) material. However, to illuminate the advantage of combining low sulfur and double vacuum melting, the J-K limits displayed within the hyperlink entitled "Micro-Cleanliness Double Vacuum Melt" apply for 316L-SCQ stainless (VIM + VAR).

The two issues most frequently questioned are weldability and machinability. For further information regarding these issues, refer to the machinability and welding sections under the workability section of this data sheet.

Considerable experience has demonstrated that the increased purchase price and machining costs associated with double vacuum melted ultra-low sulfur is more than offset by the ability to consistently achieve an exceptional electro-polished finish.

### Other Information

#### Metallurgical Requirements

##### Micro-Cleanliness Double Vacuum Melt

Sulfides		Alumina		Silicates		Oxides	
Thin	Thick	Thin	Thick	Thin	Thick	Thin	Thick
1	1	1	1/2	1	1/2	1	1

##### Micro-Cleanliness Single Vacuum Melt

Sulfides		Alumina		Silicates		Oxides	
Thin	Thick	Thin	Thick	Thin	Thick	Thin	Thick
No Guarantee		1 1/2	1	1 1/2	1	1 1/2	1

#### Applicable Specifications

- AMS 5653
- ASTM A276
- ASTM A479
- QQ-S-763
- ASTM A182
- ASTM A314
- MIL-S-862

#### Forms Manufactured

- Bar-Flats
- Wire-Shapes
- Bar-Rounds

#### Technical Articles

- [Selecting Optimal Stainless Steels for Bio-Pharmaceutical Service](#)
- [Selecting Stainless Steels for Valves](#)
- [Specialty Stainless Solves Galling, Contamination Problems of Threaded Parts for Semiconductor Industry](#)

#### Disclaimer:

The information and data presented herein are typical or average values and are not a guarantee of maximum or minimum values. Applications specifically suggested for material described herein are made solely for the purpose of illustration to enable the reader to make his/her own evaluation and are not intended as warranties, either express or implied, of fitness for these or other purposes. There is no representation that the recipient of this literature will receive updated editions as they become available.

Unless otherwise specified, registered trademarks are property of CRS Holdings Inc., a subsidiary of [Carpenter Technology Corporation](#)  
Copyright © 2020 CRS Holdings Inc. All rights reserved.

Visit us on the web at [www.carttech.com](http://www.carttech.com)

Edition Date: 3/15/04